

AD Maxdura[®] Tire Tag

Overview

Frequency Band (Operation Frequency)

860 – 960 MHz

Typical min. 4 meters vulcanized in tire,
depending on embedding position

Chip

Impinj M730

Hard Tag Dimensions

43 x 1.5 mm (+/- 0.5 mm) /

1.693 x 0.059 in

International Standard

Compliant to GS1 Class 1 Gen 2 V2
and ISO 18000-6C

Industry Segments

Automotive

Industrial Applications

Applications

Automotive Tire Tagging

Inventory and Logistics

Item Level Inventory Accuracy

Supply Chain Management

Warehouse Management



Robust tire tag is embedded for life

An embedded UHF tire tag is intended to be integrated into the tire mold prior to the manufacture and curing of the tire. It is attached to the tire directly, during tire vulcanization, so that it can be fully connected to the core of the tire and function correctly to track the tire. The use of an embedded tire tag controls the complete lifecycle of the tire from production to recycling (environment control). It supports maintenance recording, inventory tracking and fleet management, and facilitates several additional different business models. Being exposed to harsh environmental conditions during the manufacturing process as well as on the road, an RFID tire tag needs to be robust. Avery Dennison Smartrac's AD Maxdura[®] Tire Tag uses an automatic overmolding and resistance welding method to ensure highly durable and uniform antenna connections.

Typically, the IC module of common tire tag products is a small printed circuit board larger than the diameter of the spring antenna. However, tire manufacturers nowadays require much smaller dimensions to maximize homogeneity within the tire composites. To reduce overall dimensions, the AD Maxdura[®] Tire Tag is built up with a customized IC housing based on lead frame technology.

One of the most challenging issues is the adjustment of the antenna's resonance frequency when the tag is embedded inside the tire. As every customer uses its own specific rubber compound, the antenna length needs to be tailored to the specific material properties. As one of the leading automotive suppliers of RFID solutions, we have more than 20 years' experience in the field. We have leveraged our strong experience in designing RFID products for the world's largest car manufacturers to develop the AD Maxdura[®] Tire Tag.

Technical features

Chip	Impinj M730
EPC and User Memory	128-bit and 0-bit
TID Memory	96-bits of serialized TID with 48-bit serial number, 32-bit shared access and 32-bit shared kill password
Product Code	510050
Air Interface Protocol	Compliant to GS1 Class 1, Gen 2 and ISO 18000-6C
Operation Frequency	860 - 960 MHz (@23 °C +/-5 °C) / @73.4 °F, 41 / 23 °F
ESD	ESD 61000-4-2, Level 1
Hard Tag Dimension	43 x 1.5 mm (+/-0.5 mm) / 1.693 x 0.059 in
Thickness Diameter	1.5 mm (+/- 0.2 mm) / 0.059 in
Housing Material	Epoxy
Color	Black
Weight	Less than 2 gram
Operating Temperature	-30 °C to 85 °C / -22 °F to 185 °F
Storage Temperature	-40 °C to 120 °C / -40 °F to 248°F Typical storage temp. 25 °C / 77 °F
Cold Temperature Test	-40 °C (40 °F), 24 hours
High Temperature Test	120 °C (248 °F), 24 hours
Vulcanization Temperature	200 °C (392 °F), 30 mins, up to 5 MPa pressure, 2 cycles
Certificates	ISO 9001 / ISO 14001 / IATF 16949 / ISO 18000-6C / ISO 20909 / ISO 20910 / ISO 20911 / ISO 20912

Contact information

rfid.averydennison.com/contact

North America: +1-866-903-7343 (toll free US)

International: +1-678-617-2359

Connect with us on:



© 2024 Avery Dennison Corp. All rights reserved. 170 Monarch Lane, Miamisburg, OH 45342, USA Third party trademarks and/or trade names used herein are the property of their respective owner(s). Some of the trademarks appear for identification purposes only.

Warranty: Please refer to Avery Dennison standard terms and conditions: rfid.averydennison.com/termsandconditions

Care and handling: RFID inlays are sensitive to ESD. Observe standard industry practices relating to electronics / RFID to keep environmental impact and static charge to a minimum.

Applications: This product should be tested by the customer / user thoroughly under end use conditions to ensure the product meets the particular requirements. Avery Dennison does not represent that this product is fit for any particular purpose or use. Avery Dennison reserves the right to modify, change, supplement or discontinue product offerings at any time without notice. The information contained herein is believed to be reliable but Avery Dennison makes no representation concerning the accuracy or correctness of the data.

